

**FT.03.03.02.03**

**DE-ICING SALT T10**

EDITED	REVISED	APPROVED
Esther Fabregat	Ingrid Picas David Robles	Cristina Arespa
Date: 29/08/2016	Date: 30/08/2016	Date: 30/08/2016

## PRODUCT SPECIFICATION

CHANGES CONTROL		
REVISION	DATE	CHANGES
0	04/01/2012	Application: New product
1	21/06/2013	Revision of product specification. Change code
2	30/10/2014	New format and company name
3	30/08/2016	Particle size distribution adjustment to sales requirements

**FT.03.03.02.03**

**DE-ICING SALT T10**

## DE-ICING SALT T10

### Typical chemical analysis

(% of dry)

=====

Total chlorides expressed as NaCl	93-96 %
Insoluble	0.8%
Moisture	2.5%
Ion Hexacyanoferrate	Minimum 10 ppm

### Typical particle size distribution

=====

#### Mesh size (mm)

% retained

>10,00	0
>6,30	5-25
>2,36	30-70
>0,30	Min. 80

### Physical properties

=====

Bulk density	1,25 T/m <sup>3</sup>
Angle of repose	36°